


**METHOD OF PRODUCTION OF NON-STEAM-AND-PRESSURE CURED CONCRETE AND COMPOSITION OF MIXTURE OF SUCH CONCRETE**

<b>Publication number:</b> RU2243189 (C1)	<b>Also published as:</b>
<b>Publication date:</b> 2004-12-27	 RU2003124027 (A)
<b>Inventor(s):</b> VLADIMIROVA E B [RU]; KRASIL NIKOVA O B [RU]; NURUMBETOV N V [RU]; UFIMTSEV V M [RU]	
<b>Applicant(s):</b>	
<b>Classification:</b>	
<b>International:</b> C04B38/02; C04B38/02; (IPC1-7): C04B38/02	
<b>European:</b>	
<b>Application number:</b> RU20030124027 20030730	
<b>Priority number(s):</b> RU20030124027 20030730	

**Abstract of RU 2243189 (C1)**

FIELD: manufacture of building materials; production of air-entrained (cellular) concrete; manufacture of wall members. ^ SUBSTANCE: proposed method includes proportioning of cement, silica component, gas-forming agent, additives and water followed by stirring the mix simultaneously with hydromechanical activation; additives are proportioned additionally; duration of activation is 5 to 10 minutes; gas-forming agent is introduced in 2-3 minutes before its completion. Mixture for production of non-steam-and-pressure cured aerated concrete containing cement, silica component in form of ash from thermoelectric station or fine sand, building gypsum, gas-forming agent, plasticizer and water; gas-forming agent is aluminum powder or paste; activating additive is soda sulfite waste of alumina production process or another product containing sodium sulfate at the following relationship of components, mass-%: cement, 48-52; silica component, 10-14; water, 35-37.5; gas-forming agent, 0.04-0.06; building gypsum, 1.2-1.4; activating additive, 1.2-1.4; plasticizer, 0.25-0.35. ^ EFFECT: fast hardening of mixture; enhanced strength and density of concrete. ^ 3 cl, 1 tbl

Data supplied from the esp@cenet database — Worldwide